



# CRACK FILLER

## POURABLE RUBBERIZED SEALER

### BLACK ASPHALT FILLS AND SEALS CRACKS

- PREVENTS PENETRATION OF WATER
- REDUCES STRESSING, HEAVING AND WASHOUT
- STIR THOROUGHLY BEFORE USE

### DANGER

Causes serious eye damage. Causes skin irritation. May cause respiratory irritation. Causes damage to organs (Lung) through prolonged or repeated exposure (inhalation).

**KEEP OUT OF REACH OF CHILDREN**

**NET CONTENTS: 5 GALLONS**



**WARNING:** Causes skin irritation.

**STORAGE:** Store in a cool place away from excessive heat or strong oxidants. Keep from freezing. Keep away from children. Keep lid on container when not in use.

**DISPOSAL:** Empty containers or liners may retain product residues. Recommend crushing, puncturing or other means to prevent unauthorized use of containers.

**CRACK FILLER** prevents water and petroleum spills from seeping underneath pavement to the substrate. By keeping the substrate dry and clean, **CRACK FILLER** stops problems such as washout, compaction, stressing and heaving. Careful sealing of cracks assures the longest possible life for asphalt and concrete pavement. **CRACK FILLER** remains soft and pliable after drying so cracks remain sealed when pavement expands and contracts with changing weather.

### DIRECTIONS:

Remove all dirt, gravel and foreign matter from cracks by sweeping or compressed air. Stir thoroughly and apply **CRACK FILLER** to cracks with suitable pouring

can with spout. Use care to fill cracks completely without spreading excess material on pavement. **CRACK FILLER** may be leveled with squeegee. For cracks 1/2" or larger, mix 10 pounds of dry mason sand in 5 gallons of **CRACK FILLER** with enough water to make a pourable slurry. Wash tools with detergent and water immediately after use.

**CRACK FILLER** is ideal for sealing potholes before filling with **ALL WEATHER PATCH**. Just spread in clean pothole, then fill with patch according to directions. Tracking problems and rackiness may be completely eliminated by sprinkling surface of **CRACK FILLER** with sand.

Do not apply if rain threatens within 24 hours or temperature is expected to fall below 50°F. Allow 24 hours drying time before opening filled area to traffic. Do not use for sealing asphalt surface. **KEEP FROM FREEZING.**

### INGREDIENTS/CAS#:

Petroleum Asphalt (8052-42-4); Water (7732-18-5); Clay (1302-78-9); Latex (9003-55-8); Biocide (55406-53-6)

### NFPA® RATINGS:

Health: 1; Flammability: 1; Reactivity: 0



Please Recycle.

1859.052915

Share Corp. • P.O. Box 245013 • Milwaukee, WI 53224 • (800) 776-7192 • www.sharecorp.com