

WHOOSH

Dry-Film PTFE Lubricant



Form: Liquid

Color: Colorless

Odor: Solvent

pH: N/A

Solubility (in water): Insoluble
(in mineral spirits): Soluble

VOC Content (% by weight): 99.5%

Flash Point (ASTM D-7821): <77°F

Specific Gravity: 0.85 g/cm³

Density: 7.09 lbs/gal

Storage Stability (at 70°F): 1 year

<u>Ingredients</u>	<u>C.A.S. #</u>
Toluene	108-88-3
Isopropanol.....	67-63-0
Polytetrafluoroethylene	9002-84-0
Carbon Dioxide (propellant)	124-38-9

Great for use on...

- Metal
- Plastics
- Wood
- Leather
- Painted surfaces
- Natural and synthetic fabrics

Provides protection for...

- Release molds
- Drawers
- Hinges
- Springs
- Pulleys
- Tools
- Chain drives
- Window glides
- Tumbler locks & assemblies

DIRECTIONS FOR USE: Shake well before using. Be sure surface is clean and dry before coating. To ensure even coating spray about 8-10 inches from the surface. Four to six light passes should build-up the required coating thickness (0.3 to 0.5 mil dry). WHOOSH is ready for use when dry to the touch - about 5 minutes at room temperature. For use as a mold or form release, be sure to completely cover all surfaces with the lubricant.

NOTE: May harm painted or waxed finishes. Always test in an inconspicuous area before use.

HMIS			NFPA		
	Severe	4	Extreme		
Health	Serious	3	High	Health.....	2
Flammability.....	Moderate	2	Moderate	Flammability.....	4
Reactivity.....	Slight	1	Slight	Reactivity.....	0
Personal Protection.....	Minimal	0	Insignificant	Special Precautions.....	None