

HIGH SOLIDS INDUSTRIAL STRENGTH SPRAY PAINT PRO YELLOW MRO INDUSTRIAL ENAMEL

Form: Aerosol

Odor: Aromatic

pH: N/A

Solubility (in water): N/A

Flash Point (ASTM D-7821): -19 °C

Specific Gravity: N/A

Storage Stability (at 70°F): 1 year

This Product Contains: **CAS#**

Acetone	67-64-1
Propane	74-98-6
Barium Sulfate	7727-43-7
n-Butane	106-97-8
Isobutyl Acetate	110-19-0

Great For Use In...

- INDUSTRIAL EQUIPMENT AND HEAVY MACHINERY
- CONSTRUCTION TOOLS AND JOB SITE STRUCTURES
- MARINE HARDWARE AND METAL COMPONENTS
- WOOD AND METAL SURFACES
- HOME GARAGES, WORKSHOPS, AND REPAIRS

Directions for Use: Surface must be clean, dry and free of rust before painting. Protect surrounding areas from spray mist. For best results, use when can is between 50°F and 90°F (10°C and 32°C). Shake can at least 1 minute after rattle is heard and occasionally during use. Spray surface with steady even strokes at a distance of 8 to 10" (20 to 25cm). Several light coats give a better finish than one heavy coat. Recoat - For best results, recoat within one hour or after 48 hours. This time varies with curing temperature, humidity, and film thickness. Test a small hidden area before recoating. If clogging develops, turn sprayhead 1/4 turn or remove and clean sprayhead slot. DO NOT stick pin or other objects into can opening. With can and sprayhead pointed away from you, reinsert sprayhead with a gentle twisting motion. To clear sprayhead for future use, turn can upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose of partially empty cans responsibly. DO NOT incinerate or compact.

CONSULT PRODUCT LABEL FOR DETAILED DIRECTIONS

HMIS			NFPA		
	Severe	4	Extreme		
Health.....	Serious	3	High	Health.....	2
Flammability.....	Moderate	2	Moderate	Flammability.....	3
Reactivity.....	Slight	1	Slight	Reactivity.....	0
Personal Protection.....	Minimal	0	Insignificant	Special Precautions.....	None